




FLAMMABILITY TEST SUMMARY

Material: MJF PA12

Post-processing: Vapor Smoothing

Test method: FMVSS 302





Flammability Test Report Summary

1. Report Details:

- Issued to: Dr. Konstantin Rybalcenko, AMT LTD
- Report Reference: R40006
- Method: FMVSS 302

2. Test Description:

- The test was conducted using the FMVSS 302 method.
- The specimen was placed horizontally in a combustion chamber and exposed to a flame for 15 seconds.
- The maximum burning length was set at 254mm.
- The specimen was conditioned for 24 hours at a temperature of 21 °C and a relative humidity of 50% before testing.

3. Sample Details:

- Sample: Vapour smoothed MJF PA12 sample
- Dimensions: 355mm x 100mm

4. Test Results:

- The sample stopped burning when the igniting flame was removed.
- The burning rate was 0 mm/min for all tests.

A handwritten signature in blue ink, appearing to read 'K. Rybalcenko', written over a light blue horizontal line.

Dr. Konstantin Rybalcenko
Chief Scientist

Date: 21/07/2023



CONTACT INFORMATION

For further information please contact AMT:

info@amtechnologies.com

EU: +44 114 3122 3344

US: +1 512 352 9393

AMT is providing this information to assist customers. It is the responsibility of each customer to determine that its particular use of AMT's post-processing is safe and technically suitable to the customer's intended applications and consistent with the relevant regulatory requirements applicable to the customer's final product. The only warranties for AMT products and services are set forth in the express warranty statements accompanying such specific products and services. Nothing herein should be construed as constituting an additional warranty. AMT shall not be liable for technical or editorial errors or omissions contained herein.